

# Contents

<i>Preface</i>	x
<b>1 Wood as a Material</b>	<b>1</b>
1.1 Cellulose	2
1.2 Grain	4
1.3 Dimensional change in wood	8
1.4 Heartwood and sapwood	10
1.5 Natural durability	13
1.6 Rays	14
1.7 Radial and tangential directions	15
1.8 Permeability in timber	16
1.9 Chapter summary	16
<b>2 More on Timber: Some Stuff About the UK Timber Trade</b>	<b>18</b>
2.1 'Wood' or 'timber'?	18
2.2 Wood species and timber trading	19
2.3 Softwoods and hardwoods	19
2.4 Some more detail on cell structure	23
2.5 Trade names and scientific names	27
2.6 A cautionary tale about timber names	28
2.7 Growth rings	31
2.8 Earlywood and latewood	32
2.9 Rate of growth in softwoods	33
2.10 Rate of growth in hardwoods	34
2.11 Chapter summary	37
<b>3 Water in Wood: Moisture Content and the Drying of Timber</b>	<b>39</b>
3.1 The definition of moisture content	39
3.2 Moisture meters	40
3.3 'Wet' or 'dry'? In-service moisture contents and 'EMC'	43
3.4 EMC	44
3.5 Specification of desired moisture content	44
3.6 Fibre saturation point	46
3.7 Shrinkage	47
3.8 Movement	48
3.9 Kiln drying	49
3.10 Air drying	53

3.11	Timescales for drying timber	54
3.12	Chapter summary	55
<b>4</b>	<b>Specifying Timber – for Indoor or Outdoor Uses</b>	<b>57</b>
4.1	British and European standards	57
4.2	Durability and treatability of different wood species	58
4.3	Use classes	59
4.4	Examples of timbers employed in different use classes	60
4.5	Hazard and risk – and their relative importance	60
4.6	Use Class 1 – examples	61
4.7	Use Class 2 – examples	64
4.8	Use Class 3 – examples	66
4.9	Use Class 4 – examples	70
4.10	Use Class 5 – examples	76
4.11	Chapter summary	78
<b>5</b>	<b>The Quality of Timber: Grading for Appearance</b>	<b>79</b>
5.1	The need for grading	80
5.2	‘Quality’ or ‘grade’?	81
5.3	Quality	82
5.4	Grade	82
5.5	The different types of grading	83
5.6	Appearance grading	83
5.7	Appearance grading: based on defects	83
5.8	Scandinavian grades	87
5.9	Unsorted, fifths and sixths	88
5.10	Russian softwood qualities	89
5.11	European appearance grading	90
5.12	North American softwood appearance grades	90
5.13	Clears, merchantable and commons	92
5.14	A comparison of Scandinavian grades and North American grades	93
5.15	Appearance grading: based on ‘cuttings’	93
5.16	The NHLA grades	94
5.17	FAS, selects and commons	96
5.18	Selects	96
5.19	‘FIF’	97
5.20	Prime and Comsel grades	97
5.21	Malaysian grades	98
5.22	Prime, select and standard	98
5.23	‘PHND’, ‘BHND’ or ‘sound’	99
5.24	Rules are made to be bent! (within reason)	99
5.25	Shipper’s usual	99
5.26	BS EN 942: the quality of timber in joinery	100
5.27	J classes	100

5.28	'Exposed face'	101
5.29	Chapter summary	102
<b>6</b>	<b>Strength Grading and Strength Classes of Timber</b>	<b>104</b>
6.1	Appearance versus strength	106
6.2	Visual strength grades	107
6.3	GS and SS strength grades	107
6.4	Strength classes for softwoods	108
6.5	BS EN 1912	108
6.6	SC3, SC4: C16 and C24	109
6.7	Machine grading	110
6.8	Other strength grades: Europe and North America	112
6.9	Select structural, No. 1 and No. 2 structural and stud grades	112
6.10	TR26	113
6.11	Specifying the strength class or the wood species: some things to think about	114
6.12	Hardwood strength grades	115
6.13	Tropical hardwoods	116
6.14	Temperate hardwoods	116
6.15	The 'Size effect'	117
6.16	Hardwood strength classes	118
6.17	The marking of strength graded timber	119
6.18	Chapter summary	120
<b>7</b>	<b>Wood Preservatives and Wood Finishes</b>	<b>122</b>
7.1	Treat the timber last!	122
7.2	Wood preservative types	123
7.3	'Old' and 'new' types of treatments	124
7.4	The basic methods of timber treatment	124
7.5	Low pressure treatment	125
7.6	High pressure treatment	126
7.7	Preservative chemicals	126
7.8	CCA preservatives	126
7.9	The 'environmentally-friendly' preservatives	127
7.10	'Tanalised' timber	128
7.11	Organic compounds	128
7.12	'Treated' timber	129
7.13	'Wood finishes'	129
7.14	Wood in exterior uses	130
7.15	Exterior finishes	131
7.16	Varnish – and paint	131
7.17	'Microporous' exterior stains and paints	133
7.18	Non-film-forming finishes	133
7.19	Exterior paints	134
7.20	The durability of exterior finishes	135

7.21	The effects of lighter or darker colours	136
7.22	Chapter summary	137
<b>8</b>	<b>Principal Softwoods Used in the UK</b>	<b>139</b>
8.1	European redwood ( <i>Pinus sylvestris</i> )	139
8.2	European whitewood (mostly <i>Picea abies</i> )	141
8.3	Sitka spruce ( <i>Picea sitchensis</i> )	142
8.4	Western hemlock ( <i>Tsuga heterophylla</i> )	142
8.5	'Douglas fir' ( <i>Pseudotsuga menziesii</i> )	143
8.6	Larch (mainly <i>Larix decidua</i> and <i>L. kaempferi</i> / <i>L. leptolepis</i> )	145
8.7	'Western red cedar' ( <i>Thuja plicata</i> )	145
8.8	Southern pine ( <i>Pinus spp</i> – principally <i>Pinus elliottii</i> and <i>P. palustris</i> )	146
8.9	Yellow pine ( <i>Pinus strobus</i> )	147
8.10	'Parana pine' ( <i>Araucaria angustifolia</i> )	147
8.11	Species groups	148
8.12	Spruce-pine-fir	148
8.13	Hem-fir	149
8.14	Douglas fir-larch	149
<b>9</b>	<b>A Selection of Hardwoods Used in the UK</b>	<b>150</b>
9.1	Ash, American ( <i>Fraxinus spp</i> )	151
9.2	Ash, European ( <i>Fraxinus excelsior</i> )	152
9.3	Beech, European ( <i>Fagus sylvatica</i> )	152
9.4	Birch, European (mainly <i>Betula pubescens</i> )	153
9.5	Cherry, American ( <i>Prunus serotina</i> )	153
9.6	Chestnut, Sweet ( <i>Castanea sativa</i> )	153
9.7	Ekki ( <i>Lophira alata</i> )	154
9.8	Greenheart ( <i>Ocotea rodiaei</i> )	154
9.9	Idigbo ( <i>Terminalia ivorensis</i> )	155
9.10	Iroko ( <i>Milicia excelsa</i> )	155
9.11	Keruing ( <i>Dipterocarpus spp.</i> )	156
9.12	Mahogany, African ( <i>Khaya ivorensis</i> and <i>K. anthotheca</i> )	156
9.13	Mahogany, American ( <i>Swietenia macrophylla</i> )	156
9.14	Maple ( <i>Acer saccharum</i> )	157
9.15	Meranti ( <i>Shorea spp.</i> )	157
9.16	Oak, American red (principally <i>Quercus rubra</i> and <i>Q. falcata</i> )	158
9.17	Oak, American white (principally <i>Quercus alba</i> , <i>Q. prinus</i> , <i>Q. lyrata</i> and <i>Q. michauxii</i> )	158
9.18	Oak, European (mainly <i>Quercus robur</i> )	158
9.19	Obeche ( <i>Triplochiton scleroxylon</i> )	159
9.20	Opepe ( <i>Nauclea diderrichii</i> )	160
9.21	Sapele ( <i>Entandrophragma cylindricum</i> )	160
9.22	Tatajuba ( <i>Bagassa guianensis</i> )	161

9.23	Teak ( <i>Tectona grandis</i> )	161
9.24	Utile ( <i>Entandrophragma utile</i> )	161
9.25	Walnut, American ( <i>Juglans nigra</i> )	162
9.26	Walnut, European ( <i>Juglans regia</i> )	162
9.27	Whitewood, American, or Tulipwood ( <i>Liriodendron tulipifera</i> )	163
<b>10</b>	<b>Wood-based Sheet Materials</b>	<b>164</b>
10.1	Plywood	164
10.2	The two fundamental properties of plywood	165
10.3	Basic types of plywood	166
10.4	Conifer plywoods	166
10.5	Temperate hardwood plywoods	168
10.6	Tropical hardwood plywoods	168
10.7	Plywood glue bond and 'WBP'	169
10.8	Exterior	170
10.9	Adhesives used in plywood	171
10.10	BS 1088 marine plywood	172
10.11	Plywood face quality	172
10.12	Appearance grading of face veneers	173
10.13	Conifer plywood appearance grades	173
10.14	Temperate hardwood plywood appearance grades	175
10.15	Tropical hardwood plywood appearance grades	175
10.16	Particleboards and wood chipboard	177
10.17	Flaxboard and bagasse board	178
10.18	OSB	178
10.19	Fibreboards	181
10.20	Hardboard, medium board and softboard	181
10.21	MDF	183
10.22	Chapter summary	185
	<b>Appendices</b>	<b>186</b>
1	A Glossary of Wood and Timber Terms Used in the Timber and Construction Industries	186
2	A Select Bibliography of Some Useful Technical References About Wood	200
3	Some Helpful Technical, Advisory and Trade Bodies Concerned with Timber	201
	<i>Index</i>	202